



THE **LARGE-SCALE** FFF 3D-PRINTER  
FOR **PROFESSIONAL** AND **INDUSTRIAL** USE.

TECHNICAL DATA SHEET  
**BigRep PLX**

PLX is a 3D biomaterial grade filament combining resistance, mechanical rigidity and fast printability.

**Physical Properties**

<b>Material</b>	<b>PLA</b>
<b>Filament Net Weight:</b>	<b>2.5, 4.5 and 8.0 kg</b>
<b>Diameter</b>	<b>2.85 mm</b>
<b>Density</b> (ISO 1183)	<b>1.25 g/cm<sup>3</sup></b>
<b>Melting temperature</b> (DSC)	<b>170 - 190 °C</b>
<b>Vicat Softening Temperature</b> (ISO 306)	<b>n.a. °C</b>

**Recommended Printing Conditions** (Original BigRep factory files for the material are available from BigRep Global Support)

<b>Nozzle temperature</b>	<b>200 - 220 °C</b>
<b>Heating bed temperature</b>	<b>50 - 70 °C</b>
<b>Environmental temperature</b>	<b>n.a. °C</b>
<b>Printing speed</b>	<b>&gt;40 mm/s</b>
<b>Additional Comments</b>	<b><i>Material is sensitive to moisture and should be stored under dry conditions at all times</i></b>

## Mechanical Properties (Dry State)

<b>Young's Modulus</b> (ISO 527)	<b>3150 MPa</b>
<b>Tensile Strength</b> (ISO 527)	<b>48 MPa</b>
<b>Elongation at break</b> (ISO 527)	<b>20 %</b>
<b>Bending Modulus</b> (ISO 178)	<b>2580 MPa</b>
<b>Bending Strength</b> (ISO 178)	<b>95 MPa</b>
<b>Charpy Impact strength</b> (ISO 179)	<b>20 kJ/m<sup>2</sup></b>
<b>HDT / B</b> (ISO 75)	<b>n.a. °C</b>

Keep sealed in an air tight container, away from humidity.  
Store at around room temperature and protect from direct heat or sunlight.

**BigRep GmbH**  
Gneisenaustraße 66  
10961 Berlin – German

BigRep GmbH Management: Martin Back, Court of Registration: Amtsgericht Charlottenburg HRB 155360B Registered Office: Berlin



[www.sourcegraphics.com](http://www.sourcegraphics.com) | 800.791.9042